

Two Component Condensation Cure Silicone

| Product No. | Features | Color | Viscosity(cps) Ti | Mix Ratio | Pot Life (hr) | Surface Dry Time (hr) | Initial curing time (hr) | Curing depth mm | CTE ppm(<Tg) / ppm(>Tg) | Hardness Shore 00 | Surface Resistivity , (ohm) \ Volume Resistivity, (ohm-cm) | Dielectric Constant (1KHz) | Dielectric Strength (KV/mm) | Temperature Range (°C) | Storage / Shelf Life |
|-------------|-------------------------------|--------------------------|-------------------------|--------------|------------------|-----------------------------|--------------------------------|--------------------|-------------------------------|----------------------|--|------------------------------------|------------------------------------|---------------------------|----------------------|
| FX0703BLAB | Low Viscosity, Easy defoaming | A: Black B: Colorless | A: 5,500~8,500 B: <5 | 20:1 | 1 | 4 | 12 | 7mm , 7~10days | 135 / 180 | 78 | 2.0×10^{12} \ 2.2×10^{11} | 3.2 | 15 | -40 ~ + 200 | 14~34°C /6Months |
| FX0992AB | Low Viscosity, Easy defoaming | A: Black B: Colorless | A: 1,800~2,800 B: <5 | 10:1 | 1 | 4 | 12 | 7mm , 7~10days | 167 / 183 | 75 | 2.0×10^{12} \ 1.9×10^{11} | 2.8 | 12 | -40 ~ + 200 | 14~34°C /6Months |
| FX0992BLAB | Low Viscosity, Easy defoaming | A: Black B: Colorless | A:2,200~3,300 B:<5 | 10:1 | 1 | 3 | 12 | 7mm , 7~10days | 167 / 195 | 75 | 2.0×10^{12} \ 1.9×10^{11} | 2.4 | 15 | -40 ~ + 200 | 14~34°C /6Months |
| FX0992WAB | Low Viscosity, Easy defoaming | A: Black B: Colorless | A: 1,800~2,800 B: <5 | 10:1 | 1 | 3 | 12 | 7mm , 7~10days | 167 / 193 | 75 | 2.0×10^{12} \ 1.9×10^{11} | 2.5 | 14 | -40 ~ + 200 | 14~34°C /6Months |
| FX124-2 | Low Viscosity, Easy defoaming | A: Black B: Colorless | A:2,200~3,300 B:<5 | 10:1 | 0.4 | 0.8 | 6 | 7mm , 7~10days | 167 / 183 | / | 2.0×10^{12} \ 1.9×10^{11} | 3.2 | 14 | -40 ~ + 200 | 14~34°C /6Months |
| FX124-4 | Low Viscosity, Easy defoaming | A: Black B: Colorless | A:2,200~3,300 B:<5 | 10:1 | 0.4 | 0.8 | 6 | 7mm , 7~10days | 135 / 180 | / | 2.1×10^{12} \ 2.2×10^{11} | 2.1 | 15 | -40 ~ + 200 | 14~34°C /6Months |

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge.

Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.