

# **Araldite** 2050

Fast bonding. Anytime. Anywhere.



# Araldite 2050


# Fast bonding. Anytime. Anywhere.

## **Typical product characteristics**


Pot life at RT	2 min
Fixture time at RT	9 min
Processing temperature	-20 to 25°C (-4 to 77°F)
Maximum service temperature	120°C (248°F)
Tensile strength	40 MPa (5,800 psi)
Tensile modulus	1,700 MPa (246,500 psi)
Elongation at break	ca. 10%

### Lap Shear Strength at 23°C

ISO 4587




### Fixture time at different temperatures



#### Lap shear Strength after accelerated ageing

Cataplasma ageing: ISO 9142-E2



Learn more at www.aralditeadhesives.com

SF: Substrate failure

For any other information, please send an e-mail to advanced\_materials@huntsman.com

Responsible Care



Europe +41 61 299 20 41 India, Middle East, Africa & Turkey + 91 22 4095 1556 Asia / Pacific + 86 21 2208 7588 Americas +1 888 564 9318

Legal information All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries. Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials (LC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials (hornows). The following supercedes Buyer's documents: While the information and recommendations included in this publication are, to the best of Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials (hornows). The following supercedes Buyer's documents: While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL, PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY OR PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patient or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights. The Product may be or become heazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman co