

Vitrobond Hot Melt Adhesives

Part No	Base	Colour	Viscosity, CPS	Softening Point °C	Melting Point °C	Open Time. Seconds	Set Time. Seconds
Vitrobond AE 121	EVA	White	15'000	86	150	45	15 -20
Vitrobond HMA 705	EVA	White	4'500	80	160	30	15
Vitrobond HMA 8001	APAO	White	5'500 - 7'000	110	170	80	3-4
Vitrobond HMA 8002	Polyester	White	18'000 - 30'000	145	170	300	8
Vitrobond HMA 8003	APAO	White	2'000 - 3'000	140	170	15	5
Vitrobond HMA 8003-PS		Amber Transparent	7'000 - 10'000	94	160	60	NA
Vitrobond HMA 8004	Metallocene Polyolefin	White Transparent	700 - 1'100	105	170	60	2
Vitronbond HMA 8005	APAO	Slight Amber	2'500	140	170	70	20
Vitrobond HMA 8016	APAO	White	3'500 - 5'000	115	170	10 -20	3-6

All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge.

Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights.

We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.