



Advanced Materials

Araldite[®] adhesives
Strength in bonding 2000+



Adhesives
selector guide



Properties and performance

	Chemical type	Key features	Metals					
			Mild steel	Stainless steel	Aluminium	Copper	Brass	Galvanized steel
Conditions								
Unit								
Araldite® 2011	EP	<ul style="list-style-type: none"> > Multi purpose > Long working life > Good resistance to dynamic loading 	●●●	●●●	●●●	●●●	●●●	●●●
Araldite® 2012	EP	<ul style="list-style-type: none"> > Fast curing > General purpose > Good long term durability 	●●●	●●●	●●●	●●	●●●	●
Araldite® 2013	EP	<ul style="list-style-type: none"> > Metal coloured paste > Suitable for vertical applications > Good environmental, chemical and temperature durability 	●●●	●●●	●●●	●●	●●	●●●
Araldite® 2014-1	EP	<ul style="list-style-type: none"> > Grey paste > High temperature and chemical resistance > Excellent durability on metals and against many chemicals 	●●●	●●●	●●●	●●	●●	●
Araldite® 2015	EP	<ul style="list-style-type: none"> > Toughened paste > Ideal for GRP, SMC and dissimilar substrates > Excellent resistance to dynamic loading 	●●●	●●●	●●●	●●●	●●●	●
Araldite® 2031	EP	<ul style="list-style-type: none"> > Toughened adhesive, resilient bond > Suitable for metal and composite bonding, good adhesion onto polyamides 	●●	●●●	●●	●●●	●●●	●●
Araldite® 2018	PUR	<ul style="list-style-type: none"> > Good UV stability > Ideal for bonding thermoplastics > Long working life 	●●	●	●	●	●	●●
Araldite® 2028-1	PUR	<ul style="list-style-type: none"> > Transparent > Fast curing > UV stable 	●●	●●	●●	●	●	●●●
Araldite® 2029	PUR	<ul style="list-style-type: none"> > Medium open time > Designed to bond composites and metals > Well balanced strength and durability 	●●●	●●●	●●●	●●●	●●	●●●
Araldite® 2021	MMA	<ul style="list-style-type: none"> > Rapid curing > High peel and shear strength > Multi purpose 	●●●	●●●	●●●	●●	●	●●
Araldite® 2022	MMA	<ul style="list-style-type: none"> > Ideal for bonding thermoplastics > Multi purpose > Good sanding properties 	●●●	●●●	●●●	●●	●●	●●●
Araldite® 2047-1	MMA	<ul style="list-style-type: none"> > Outstanding adhesion to copper, brass, galvanized and stainless steel > Requires minimal surface treatment > Gap filling up to 5 mm 	●●	●●●	●●	●●●	●●●	●●●
Araldite® 2048	MMA	<ul style="list-style-type: none"> > Tolerant to "less than ideal" pretreatment > Gap filling up to 8 mm > Tough flexible bonds for use in dynamic environment 	●●	●●●	●●●	●●●	●●●	●●
Araldite® 2052-1	MMA	<ul style="list-style-type: none"> > Very high temperature and chemical resistance > Tolerant to "less than ideal" pretreatment > Excellent on metals 	●●	●●●	●●●	●●●	●●●	●

Thermosets / composites				Thermoplastics					Miscellaneous substrates				Viscosity	Work time	
GRP (UP)	GRP (EP)	CFRP	SMC	PVC	PA	ABS, ASA, SAN	PC	PMMA	Ceramic	Glass	Rubber	Wood			
														Pot life (100 g at 23°C)	
														Pa·s	min
••••	••••	••••	••••	•	••	••••	••	•	••••	••••	••••	••••	40	100	
••••	••••	••	••	••	•	••	••	•	••••	••••	•	••••	30	6	
••••	••	••	••••	••••	•	•	•	••	••••	••••	•	••••	thixotropic	65	
••••	••••	••	••••	••	•	••	•	•	••	••••	••	••••	thixotropic	60	
••••	••••	••••	••••	••	•	••	••	••	••••	••••	••	••••	thixotropic	35	
••••	••••	••	••••	••	••••	••	••	•	••••	••••	••	••••	thixotropic	60	
••••	••••	••••	••••	••	••	••••	••••	••	••	••	••••	••	8	40	
••••	••••	••••	••••	••••	••	••••	••••	••	••	••	••	••	5	6	
••••	••••	••••	••	••••	••	••••	••••	••••	••	••	••	••	thixotropic	40	
••••	••	••	••	••••	••	••	••••	••••	••••	••••	••	•	thixotropic	3	
••••	••	••	••	••••	•	••••	••••	••••	••••	••	••	•	thixotropic	10	
••	•	•	••	••••	•	••••	••••	••••	••	••	••	•	thixotropic	5	
••	••••	••••	••••	••••	•	••••	••••	••••	••	••	••	•	thixotropic	10	
•	•	•	•	••	•	••••	••	••••	••••	••••	•	•	thixotropic	15	

The data below indicates the detailed properties and performance of each product. This data was obtained following recommended pre-treatment of substrates.

Cure speed	Mechanical properties		Bond strength	Durability in			Colour (mixed)	Packaging				
								50ml	200ml	380ml	480ml	WP (2kg)
Cure time at 23°C to LSS* = 1 N/mm ²	E-modulus at 23°C	Elongation at break at 23°C	LSS* aluminium at 23°C	Water/humidity	Chemicals	Heat						
min	N/mm ²	%	N/mm ²									
420	1900	9	26	●	●●	●●	yellow	○	○	○		○
20	2520	4	18	●●	●●●	●●	yellow	○	○			○
240	1300	1	18	●●	●●	●●	grey	○	○	○		○
180	4000	1	19	●●●	●●●	●●●	grey	○	○	○		○
240	2000	4	16	●●●	●●●	●●●	beige	○	○	○		○
360	1000	5	19	●●●	●●●	●●●	black	○		○		
240	16	45	7	●●	●	●●	colourless		○			
15	16	60	15	●	●	●●	transparent	○				
240	580	39	25	●●	●●	●●●	grey	○				
8	2300	5	23	●●	●●	●●●	yellow	○		○		
18	2050	3	25	●●	●	●●●	yellow	○		○		
15	850	15	19	●●	●●	●●	brown	○				○
15	360	91	24	●●	●	●●●	red	○				○
20	1750	7	24	●●	●●●	●●●	red					○

* LSS = Lap Shear Strength

Key questions

Adhesives	Epoxy	Methacrylate	Polyurethane
	Load-bearing adhesives good for metals and composites	Fast setting and resilient for composites, thermoplastics and metals	Flexible adhesive for composites and certain thermoplastics
1. Do you require a multi-purpose adhesive with a rapid cure?	Araldite® 2012	Araldite® 2047-1	–
2. Do you require a multi-purpose adhesive with a long working life?	Araldite® 2011	–	Araldite® 2029
3. Do you require a fast cure adhesive?	Araldite® 2012	Araldite® 2021 Araldite® 2047-1	Araldite® 2028-1
4. Do you have large areas for bonding and/or require a long working time?	Araldite® 2013 Araldite® 2014-1 Araldite® 2031	–	Araldite® 2029 Araldite® 2018
5. Do you require high toughness and the ability to bond different substrates?	Araldite® 2015 Araldite® 2031	Araldite® 2022 Araldite® 2048 Araldite® 2047-1	Araldite® 2029
6. Do you require chemical resistance or performance at high temperatures?	Araldite® 2014-1	Araldite® 2052-1	–
7. Do you require an adhesive for gap filling or vertical applications?	Araldite® 2013 Araldite® 2014-1 Araldite® 2015 Araldite® 2031	Araldite® 2021 Araldite® 2022 Araldite® 2047-1 Araldite® 2048	Araldite® 2029
8. Do you require a flexible adhesive?	–	Araldite® 2048	Araldite® 2018 Araldite® 2028-1
9. Do you require a transparent adhesive?	–	–	Araldite® 2028-1

Huntsman Advanced Materials

Our Advanced Materials division is a leading global chemical solutions provider with a long heritage of pioneering technologically advanced epoxy, acrylic and polyurethane-based polymer products.

Our capabilities in high-performance adhesives and composites, delivered by more than 2300 associates, serve over 3000 global customers with innovative, tailor-made solutions and more than 1500 products which address global engineering challenges.

Global presence – 13 manufacturing sites



Distributed by

intertronics
adhesives, coatings, sealants & equipment
for your manufacturing and technology applications
t 01865 842842
e info@intertronics.co.uk
www.intertronics.co.uk

Mobile App from Huntsman Advanced Materials

Download our mobile App and easily find the adhesive to fulfill your need.



HUNTSMAN

Enriching lives through innovation

For more information

www.huntsman.com/advanced_materials
advanced_materials@huntsman.com

Europe

Huntsman Advanced Materials (Switzerland) GmbH
Klybeckstrasse 200
P.O. Box
4002 Basel
Switzerland
Tel. +41 61 299 20 41
Fax +41 61 299 20 40

India, Middle East, Africa & Turkey

Huntsman Advanced Materials (India) Pvt. Ltd.
5th Floor, Bldg. No. 10
Solitaire Corporate Park, 167
Guru Hargovindji Marg, Chakal, Andheri (East)
Mumbai – 400 093
India
Tel. + 91 22 4095 1556
Fax + 91 22 4095 1300 / 1500

Asia / Pacific

Huntsman Advanced Materials (Guangdong) Co., Ltd.
Shanghai Suites 4604 – 4606, 46F Maxdo Center
8 Xing Yi Road
Shanghai, 200336
P.R. China
Tel. + 86 21 2208 7588
Fax + 86 21 2208 7511

Americas

Huntsman Advanced Materials Americas Inc.
10003 Woodloch Forest Drive
The Woodlands
Texas 77380
USA
Tel. +1 888 564 9318
Fax +1 281 719 4047

Legal information

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. or Huntsman Advanced Materials (Guangdong) Ltd. ("Huntsman"). The following supercedes Buyer's documents. While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, (ii) take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product and (iii) comply with and ensure that its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product comply with all safety information contained in the applicable Material Safety Data Sheets, Technical Data Sheets or other instructions provided by Huntsman and all applicable laws, regulations and standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product. Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative.

© 2013 Huntsman Corporation. All rights reserved.

Ref. No. AdMat Araldite® 2000plus selector guide 03.13_EN_EU



Registered for
REACH